

GTX MULTI-SEAL ADHESIVE SEALANT WHITE PART NO. 49391

TYPICAL PROPERTIES

Uncured

Appearance	Smooth homogenous paste
Color	White
Specific Gravity	1.5
Extrusion Rate, g/min	450
Skin Over, minutes	25
Cure Time @ (75°F & 50% RH (3/8 thickness), hours	24
VOC (g/L)	15

Cured – Physical

Durometer Hardness, Shore A, points	40
Tensile Strength (psi)	200
Elongation, percent	320



DESCRIPTION

Dynatex® White GTX Multi-Seal Adhesive Sealant is a new VOC compliant adhesive for all 50 states. GTX Sealant takes the place of most traditional sealants and is designed to resist all of the, on-the-road flexing and vibration. *Dynatex® White GTX Multi-Seal Adhesive Sealant* is fast curing and provides permanent elastic adhesion to most surfaces with excellent elasticity. *Dynatex® White GTX Multi-Seal Adhesive Sealant* is paintable within 30 minutes, non-yellowing, non-streaking, sandable, and free from solvents and isocyanates. *Dynatex® White GTX Multi-Seal Adhesive Sealant* cures on exposure to atmospheric moisture to form a durable flexible seal. It has been formulated to offer outstanding primer-less adhesion to all basic substrates found in the transportation market, such as steel, aluminum, glass, vinyl, and wood. It can be applied and tooled in almost all weather conditions. Sealant is paintable with most paints. You should fully test prior to using.

FEATURES

- Strong heavy duty multi-purpose adhesive sealant
- Solvent free with no unpleasant odor
- Compatible with most paints*
- Non-streaking or staining
- Fast cure – skin time 30 minutes
- VOC Compliant

TYPICAL APPLICATIONS

Popular applications include:

- Tractor trailers
- RV's
- Buses
- Van conversions
- Shipping containers and many other adhesive /sealant applications
- Metal to metal

* Always test small area for compatibility before applying.

STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **Dynatex® White GTX Multi-Seal Adhesive Sealant** has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the nozzle tip pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

TRANSPORTATION INFORMATION

DOT Road Shipment Information

DOT (USA) Caulking & Glaziers, NOI
DOT Hazard Classification.....None
UN/NA NumberNot applicable
Label RequiredNone
Marine Pollutant.....None

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non-warranty: Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.

Dynatex® A division of Soudal Accumetric

Dynatex

350 Ring Road
Elizabethtown
Kentucky 42701 USA
(800) 999-2937
TEL (270) 769-5557
FAX (270) 769-6418

Outside U.S.

TEL +1(270) 769-5557
FAX +1(270) 769-6418

Accumetric Asia Pacific, LTD

18 Kitpanit Bldg. 5th Floor
#502 Patpong Road
Suriyawong, Bangrak
Bangkok, 10500 Thailand
TEL (662) 634-3060
FAX (662) 634-3066

Email: sales@dynatexinc.com
Website: www.dynatexinc.com